

GLASS PUTTY

CSX-01.002 (green)

Characteristics:

Body filler with glass fibres. Easy to work and sand even with a coarse sanding paper (P120 - P150). Glass putty can be used under filler directly. Glass putty was designed for use on steel, aluminium and glass-fibre reinforced plastic. Manual / machine sanding dry. Easy to work also with homogenous surfaces even by applying thick coats. Glass putty doesn't fill the sanding paper and has very good adhesion to surface. It can be used to reinforce damaged surfaces.

Application:

The surface must be cleaned, dry, degreased and matted. Thoroughly mix putty and 2-3% of hardener BPO by weight. Apply within 5 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

Note: Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C.

Technical data:

VOC content: 2004/42/II(b)(250) <250

Glass putty CSX-01.002:

Shelf-life: 12 months Density: 1,75 g/cm³ Colour: green

Glass putty CSX-01.020:

Shelf-life: 12 months Density: 1,75 g/cm³ Colour: blue



Cleaning



Hardener addition

Glass putty	100 g
BPO Hardener	2-3 g



Body filling

3 - 5 min.



Drying time

16 - 30 min.



Hand sanding / dry

P120 - P320



Machine sanding / dry

P120 - P320



Store in cold place

Chemical Alliance Polska sp. z o.o.

ul. Prosta 23, Łozienica, 72-100 Goleniów, PL, tel. +48 91 41 65 440, fax +48 91 41 65 487
NIP 781 16 87 419 REGON 6341159570, Kapitał Zakładowy 2.000.000,00 PLN
Sąd Rejonowy w Szczecinie XVII Wydział Gospodarczy KRS 0000003186