

FINE PUTTY

CSX-01.012 (white)

Characteristics:

Fine finishing body filler. Easy to work in thin coats and sand with a coarse sanding paper (P150 - P320) what provide the highest quality of putty surface and repaired area. Coarse sanding can be replaced by fine sanding, what reduces repair process and material consumption.

Suitable for filling uneven areas and damages in paintwork and finish surfaces previously repaired with filling putties. Manual / machine sanding dry. Film thickness is 2 mm maximum. Fine putty doesn't fill the sanding paper.

Application:

The surface must be cleaned, dry, degreased and matted. Thoroughly mix putty and 2-3% of hardener BPO by weight. Apply within 5 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

Note: Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C.

Technical data:

VOC content: 2004/42/IB(b)(250) <250

Fine Putty: CSX-01.012

Shelf-life: 12 months Density: 1,87 g/cm³ Colour: white

Fine Putty: CSX-01.014

Shelf-life: 12 months Density: 1,87 g/cm³ Colour: blue

Fine Putty: CSX-01.015

Shelf-life: 12 months Density: 1,87 g/cm³ Colour: yellow



Cleaning



Hardener addition

Fine putty 100 g
BPO Hardener 2-3 g



Body filling

3 - 5 min.



Drying time

16 - 30 min.



Hand sanding / dry

P150 - P320



Machine sanding / dry

P150 - P320



Store in cold place

Chemical Alliance Polska sp. z o.o.

ul. Prosta 23, Łozienica, 72-100 Goleniów, PL, tel. +48 91 41 65 440, fax +48 91 41 65 487
NIP 781 16 87 419 REGON 6341159570, Kapitał Zakładowy 2.000.000,00 PLN
Sąd Rejonowy w Szczecinie XVII Wydział Gospodarczy KRS 0000003186