## BLACK CARBON PUTTY CSX-01.030



v.01-09-2013

## **Characteristics:**

Black Carbon Putty has got carbon fibres. It is characterized by creamy consistency, which allows easily to work in 2 - 4 mm layers and to grind with high granulation of abrasives. Possibility of using higher granulation of abrasives for pre-grinding (coarse cut P150 - P240). Adequate putty hardness to automotive coatings eliminates creation of crossings between putty and repaired surface. Due to this Black Carbon Putty can be applied also directly under filling primer. This putty is designed particularly for large repairs of very destroyed surfaces.

For filling unevenness on steel, aluminium and polyester-glass surfaces. Destined for manual / machine treatment with sanding dry materials does not fill sandpaper while grinding. Easy to work also on surfaces with complicated shapes even when applying thicker layers. It has a very good surface adhesion, designed for e.g. reinforcing damaged surfaces, increasing the mechanical strength of the repaired element.

## Application:

The surface must be cleaned, dry, degreased and matted. Thoroughly mix Black Carbon Putty and 2 - 3% of hardener BPO by weight. Apply within 4 - 6 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

**Note:** Using too much hardener can lead to topcoat discoloration. It is not recommended to use Black Carbon Putty below 15°C.

Technical data:

Shelf-life: 12 months Density: 1,82-1,84 g/cm<sup>3</sup> Colour: black

VOC content: 2004/42/IIB(b)(250) <250



## Cleaning



**Hardener addition** Black Carbon Putty 100 g

BPO Hardener 2-3 g



**Body filling** 4 - 6 min.



**Drying time** 25 - 30 min.



Hand sanding / dry P120 - P320



Machine sanding / dry P120 - P320



Store in cold place