

FILL BLACK PUTTY

CSX-01.061

Characteristics:

Fine body filler easy to work, characterized by good shaping properties in any required thickness. Suitable hardness of putty to hardness of paintwork and the smooth non-porous surface allows to use this product as filling and finishing putty. Fill putty was designed for use on steel and glass-fibre reinforced plastics.

Manual / machine sanding dry. Easy to work also with homogenous surfaces even by applying thick coats. Putty doesn't fill the sanding paper. Deep imperfections are filled in a few coats.

Application:

The surface must be cleaned, dry, degreased and matted. Thoroughly mix putty and 2-3% of hardener BPO by weight. Apply within 5 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

Note: Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C.

Technical data:

VOC content: 2004/42/II(b)(250) <250

Shelf-life: 12 months Density: 1,90 – 1,91 g/cm³ Colour: black



Cleaning



Hardener addition

Putty	100 g
BPO Hardener	2-3 g



Body filling

3 - 5 min



Drying time

20 - 30 min



Hand sanding / dry

P100 - P320



Machine sanding / dry

P100 - P320



Store in cold place

Chemical Alliance Polska sp. z o.o.

ul. Prosta 23, Łozienica, 72-100 Goleniów, PL, tel. +48 91 41 65 440, fax +48 91 41 65 487
NIP 781 16 87 419 REGON 6341159570, Kapitał Zakładowy 2.000.000,00 PLN
Sąd Rejonowy w Szczecinie XVII Wydział Gospodarczy KRS 0000003186