

UNIVERSAL PLUS PUTTY

CSX-01.067

Characteristics:

Especially creamy fill and fine putty. Adheres to all vehicle surfaces including zinc-coated. Very easy application and shaping, short drying time and excellent sanding properties are main features of this product.

Application:

The surface must be clean, dry, degreased and matted with abrasives. Thoroughly mix putty by weight with 2% of BPO hardener. Apply within 3-4 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

Note:

Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C. Do not apply over wash primers and one component acrylic products.

Technical data:

VOC 2004/42/IIIB(b)(250) max. 250g/l

Shelf-life: 12 months

Density: 1.81 – 1.83 g/cm³

Colour: beige



Cleaning



Hardener addition

Putty	100 g
BPO Hardener	2 g



Body filling

3 - 4 min



Drying time

20 min



Hand sanding / dry

P120 - P280



Machine sanding / dry

P120 - P280



Store in cold place

Chemical Alliance Polska sp. z o.o.

ul. Prosta 23, Łozienica, 72-100 Goleniów, PL, tel. +48 91 41 65 440, fax +48 91 41 65 487
NIP 781 16 87 419 REGON 6341159570, Kapitał Zakładowy 2.000.000,00 PLN
Sąd Rejonowy w Szczecinie XVII Wydział Gospodarczy KRS 0000003186