

ALU THX PUTTY

CSX-01.069

Characteristics:

Polyester aluminium-pigmented putty combining the excellent spreadability and compactness. Specially formulated to achieve resistance to high temperature and good mechanical properties. Due to this product is suitable for filling parts of steel, aluminium and zinc coated surfaces exposed to high temperature and mechanical stress.

Application:

The surface must be clean, dry, degreased and matted with abrasives. Thoroughly mix putty by weight with 2% of BPO hardener. Apply within 5-6 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

Note: Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C. Do not apply over wash primers and one component acrylic products.

Technical data:

VOC 2004/42/IIB(b)(250) max. 250g/l

Shelf-life: 12 months

Density: 1.77 – 1.79 g/cm³

Colour: silver-grey



Cleaning



Hardener addition

Putty	100 g
BPO Hardener	2 g



Body filling

5 - 6 min



Drying time

20 - 25 min



Hand sanding / dry

P120 - P280



Machine sanding / dry

P120 - P280



Store in cold place

Chemical Alliance Polska sp. z o.o.

ul. Prosta 23, Łozienica, 72-100 Goleniów, PL, tel. +48 91 41 65 440, fax +48 91 41 65 487
NIP 781 16 87 419 REGON 6341159570, Kapitał Zakładowy 2.000.000,00 PLN
Sąd Rejonowy w Szczecinie XVII Wydział Gospodarczy KRS 0000003186