

LIGHT UNIFILL PUTTY

CSX-01.071

CHARACTERISTICS

Universal ultra-light polyester putty with very good adhesion to surfaces of steel, aluminium, zinc-coated and polyester. Its creamy texture and good spreading allows easy repair of large areas. It produces a medium-soft, smooth and sealed coat suitable both for manual and machine sanding.

APPLICATION

The surface must be clean, dry, degreased and matted with abrasives. Thoroughly mix putty by weight with 2 - 3% of BPO hardener. Apply within 5 - 6 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

Note: Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C. Do not apply over wash primers and one component acrylic products.

TECHNICAL DATA

VOC 2004/42/IIB(b)(250) max. 250 g/l

Shelf life: 12 months

Density: 1.11 – 1.13 g/cm³

Colour: dark yellow



Cleaning



Hardener addition

Putty	100 g
BPO Hardener	2 - 3 g



Body filling

5 - 6 min



Drying time

20 - 30 min



Hand sanding / dry

P120 - P400



Machine sanding / dry

P120 - P400



Store in cold place

Chemical Alliance Polska sp. z o.o.

ul. Prosta 23, Łozienica, 72-100 Goleniów, PL, tel. +48 91 41 65 440, fax +48 91 41 65 487
NIP 781 16 87 419 REGON 6341159570, Kapitał Zakładowy 2.000.000,00 PLN
Sąd Rejonowy w Szczecinie XVII Wydział Gospodarczy KRS 0000003186