

LIGHT PLUS PUTTY

CSX-01.032

Characteristics:

Light Plus Putty characterized by very good adhesion to different surface, like: steel, aluminum, zinc, 2k acryl fillers and old coats. The density is 25% lower than traditional polyester putty (putty contains special light filler – micro glass bubbles). The putty has got excellence application properties. Sanding is very easy. It is especially recommended for large surfaces, such as cars roofs, doors or boats.

Application:

The surface must be cleaned, dry, degreased and matted. Thoroughly mix putty and 2-3% of hardener BPO by weight. Apply within 4 - 6 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time

NOTE: Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C

Technical data:

VOC content: 2004/42/II(b)(250) <250

Shelf-life: 12 months

Density: 1,4 - 1,5 g/cm³

Colour: yellow



Cleaning



Hardener addition

Putty	100 g
BPO Hardener	2-3 g



Body filling

4 - 6 min.



Drying time

20 - 30 min.



Hand sanding / dry

P120 - P320



Machine sanding / dry

P120 - P320



Store in cold place

Chemical Alliance Polska sp. z o.o.

ul. Prosta 23, Łozienica, 72-100 Goleniów, PL , tel. +48 91 41 65 440, fax +48 91 41 65 487
NIP 781 16 87 419 REGON 6341159570, Kapitał Zakładowy 2.000.000,00 PLN
Sąd Rejonowy w Szczecinie XVII Wydział Gospodarczy KRS 0000003186